


THREADED-END SPECIMEN GRIP (THREADS FROM 1/2" TO 1" DIAMETER)



Specimen:	Diameter	1/2" up to 1"
Fixture:	Construction	High strength steel with protective finish
	Temperature	-120 to 250°F (-85 to 122°C)
	Mounting	1.5"-6 threaded couplings
	Capacity	20,000 lbs (90kN)
	Weight	10 lbs
	Dimensions	3" x 3" x 12"
Standard	Manufactured in accordance with ASTM A370 and E8	

Model No. ASTM.E0008.21 - Threaded-End Specimen Coupling Set

Specimen diameters from 1/2" up to 1". Please specify diameter according to the part numbers in the accessories section. The loading end has a 1.5"-6 class 2B threaded coupling. The outer diameter of the coupling is supplied with a hex configuration. Each threaded coupling set is constructed from high strength steel with a protective black oxide finish in accordance with ASTM A370 and E8.

MODEL NO. ASTM.E0008.21

TENSION, TENSILE, METALLIC, MATERIALS,

ACCESSORIES

ACC.E0008.2101 - Specimen Thread - 1/2"-13
ACC.E0008.2102 - Specimen Thread - 1/2"-20
ACC.E0008.2103 - Specimen Thread - 5/8"-11
ACC.E0008.2104 - Specimen Thread - 5/8"-18
ACC.E0008.2105 - Specimen Thread - 3/4"-10
ACC.E0008.2106 - Specimen Thread - 3/4"-16
ACC.E0008.2107 - Specimen Thread - 7/8"-9
ACC.E0008.2108 - Specimen Thread - 7/8"-14

Upper and lower fixture attachment is supplied with 1.5" -6 female coupling. (Common adapter sizes include:)

Model No. M03S46 - 1.25" Male Clevis (Type D) to 1.5" -6 Threaded Stud

Model No. S46S42 - 1.5" -6 to 1.25" -12 Threaded Step Stud

Model No. S48S46 - 1.5" -12 to 1.5" -6 Threaded Step Stud

Model No. S60S46 - 2" -12 to 1.5" -6 Threaded Step Stud

SPARE PARTS

Please contact us for spare or replacement parts.

REFERENCE DOCUMENT AND TEST METHOD SCOPE:

<http://www.astm.org/Standards/E8.htm>

ASTM E8 / E8M - 15a

Standard Test Methods for Tension Testing of Metallic Materials

1.1 These test methods cover the tension testing of metallic materials in any form at room temperature, specifically, the methods of determination of yield strength, yield point elongation, tensile strength, elongation, and reduction of area.

1.2 The gauge lengths for most round specimens are required to be 4D for E8 and 5D for E8M. The gauge length is the most significant difference between E8 and E8M test specimens. Test specimens made from powder metallurgy (P/M) materials are exempt from this requirement by industry-wide agreement to keep the pressing of the material to a specific projected area and density.

1.3 Exceptions to the provisions of these test methods may need to be made in individual specifications or test methods for a particular material. For examples, see Test Methods and Definitions A370 and Test Methods B557, and B557M.

1.4 Room temperature shall be considered to be 10 to 38°C [50 to 100°F] unless otherwise specified.

1.5 The values stated in SI units are to be regarded as separate from inch/pound units. The values stated in each system are not exact equivalents; therefore each system must be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.6 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Extracted, with permission, Standard Test Methods for Tension Testing of Metallic Materials copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428. A copy of the complete standard may be purchased from ASTM International, www.astm.org.

Material Testing Technology